

PCTD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 153/00	A1	(11) International Publication Number: WO 99/03938 (43) International Publication Date: 28 January 1999 (28.01.99)
(21) International Application Number: PCT/US98/14835 (22) International Filing Date: 16 July 1998 (16.07.98) (30) Priority Data: 08/896,588 17 July 1997 (17.07.97) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: SPINELLI, Harry, J.; 4604 Big Rock Drive, Wilmington, DE 19801 (US). JAKUBAUSKAS, Henry, L.; 17 Nine Gates Road, Chadds Ford, PA 19317 (US). MCINTYRE, Patrick, F.; 2931 Rambling Way, Bloomfield Hills, MI 48302 (US). KING, James, G.; 1344 Westboro Drive, Birmingham, MI 48009 (US). (74) Agent: FRICKE, Hilmar, L.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AU, BR, CA, CN, JP, KR, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: PIGMENT DISPERSIONS CONTAINING HYDROXYLATED AB-BLOCK POLYMER DISPERSANT		
(57) Abstract <p>A pigment dispersion useful for forming coating compositions containing dispersed pigment, a carrier liquid and an AB-block polymer dispersant (binder); the AB block polymer has a number average molecular weight of about 5,000-20,000 and contains 20-80 % by weight of a polymeric A segment and correspondingly 80-20 % by weight of a polymeric B segment; wherein the polymeric A segment of the block polymer is of polymerized glycidyl (meth)acrylate monomers reacted with an acid from the group of aromatic carboxylic acids or aliphatic carboxylic acids; and the B segment is of polymerized alkyl (meth)acrylate monomers having 1-12 carbon atoms in the alkyl group, hydroxy alkyl (meth)acrylate monomers having about 1-4 carbon atoms in the alkyl group; and wherein the weight ratio of pigment to binder in the dispersion is about 1/100 - 200/100.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE**PIGMENT DISPERSIONS CONTAINING HYDROXYLATED AB-BLOCK
POLYMER DISPERSANT****TECHNICAL FIELD**

5 This invention relates to improved pigment dispersions containing an AB-block polymer dispersant.

BACKGROUND OF THE INVENTION

AB polymer dispersants are known in the art and are used to form pigment dispersions that are used in a variety of coating compositions. US Patent
10 4,656,226 issued April 7, 1987, to Hutchins et al shows an AB block polymer dispersant having polar groups such as acids or amines that attach to a pigment's surface and the other block of the polymer keeps the pigments stable in the dispersion or coating composition. US Patent 5,221,334 issued June 22, 1994, to Ma et al also shows AB or BAB block polymers that are used in aqueous printing
15 inks to keep pigments dispersed in the inks.

"Living" free radical polymerization technique, also referred to as group transfer polymerization (GTP) is a well-known technique that is used to form the aforementioned block polymers. In GTP, an initiator splits with one end going to the tail of an acrylic monomer unit and the other to the head. The group
20 at the head transfers to the head of a second monomer unit as that unit is polymerized with the first. Such techniques are described in US Patents 4,417,034 issued November 22, 1983, and 4,508,880 issued April 2, 1985, to O.W. Webster and US Patents 4,414,372 issued November 8, 1983, and 4,524,196 issued June 18, 1985 to Farnham et al. The above patents are hereby incorporated by
25 reference.

Conventional truck and automobile finishes comprise a clear coat applied over a pigmented base coat that is applied over a primer layer. The polymer dispersant used in the base coat must not only keep the pigment dispersed but needs to contain a reactive group that will react with the crosslinking agent
30 used in the coating composition which on curing makes the dispersant an integral part of the resulting finish. Polymer dispersants can cause intercoat adhesion failures and usually are used only in limited amounts. It is desirable that the polymer dispersant have reactive groups that will bond with the primer layer to improve intercoat adhesion of the base coat to the primer rather than cause
35 intercoat adhesion problems and cause flaking and chipping of the resulting finish.

SUMMARY OF THE INVENTION

A pigment dispersion useful for forming coating compositions containing dispersed pigment, a carrier liquid and an AB-block polymer dispersant (binder);

5 the AB block polymer has a number average molecular weight of about 5,000 - 20,000 and contains 20-80% by weight of a polymeric A segment and correspondingly 80-20% by weight of a polymeric B segment; wherein

10 the polymeric A segment of the block polymer is of polymerized glycidyl (meth)acrylate monomers reacted with an acid from the group of aromatic carboxylic acids or aliphatic carboxylic acids; and

 the B segment is of polymerized alkyl (meth)acrylate monomers having 1-12 carbon atoms in the alkyl group, hydroxy alkyl (meth)acrylate monomers having about 14 carbon atoms in the alkyl group; and

15 wherein the weight ratio of pigment to binder in the dispersion is about 1/100 - 200/100;

DETAILED DESCRIPTION OF THE INVENTION

20 The term (meth)acrylate refers to both the acrylate and methacrylate esters.

 The novel pigment dispersion is stable and in general is non-flocculated or agglomerated and is compatible with a variety of polymeric film forming binders that are conventionally used in coating compositions and in particular, compatible with acrylic polymers that are used in coating
25 compositions. The AB block polymer dispersant upon curing of the coating composition into which it has been incorporated, reacts with other film forming components of the coating composition and becomes part of the film and does not cause deterioration of the film upon weathering as may occur if it remained an
30 unreacted component of the film. Also, since the AB block polymer is an excellent dispersant, the ratio of polymer to pigment or polymer being dispersed is less than used with conventional dispersants and a large variety of pigments and polymers can be dispersed thereby enlarging the number and types of pigment dispersions that can be formulated. The AB block polymer has reactive groups

that improve adhesion to a primer layer thereby reducing flaking and chipping of the coating composition.

It has been found that improved coating compositions are obtained by using these novel pigment dispersions. These coating compositions also
5 contain a film forming binder usually an acrylic polymer and a curing agent such as a polyisocyanate or an alkylated melamine. Such compositions have the advantage of providing excellent coating properties desirable for automotive finishes. Base coats of conventional base coat / clear coat finishes currently used on automobiles and trucks colored with a carbon black pigment dispersion of this
10 invention have significantly improved black jetness in comparison to base coats colored with conventional carbon black pigment dispersions.

The AB block polymer used to formulate the dispersion of this invention can be prepared by anionic polymerization or by Group Transfer Polymerization techniques. Preferably, the polymer is prepared using GTP
15 techniques as described in the aforementioned GTP patents (US Patents 4,417,034, 4,508,880, 4,414,372 and 4,524,196). These polymers have a number average molecular weight of about 5,000 - 20,000, preferably about 7,500 - 15,000. The A segment of the polymer comprises about 20-80% by weight of the polymer and correspondingly the B segment of the polymer comprises about
20 80-20% by weight of the polymer.

All molecular weights referred herein are determined by GPC (gel permeation chromatography) using a polystyrene standard.

The AB block polymer has a relatively highly polar anchoring A segment and a relatively non-polar stabilizing B-segment. The A-segment is
25 designed to absorb on the surface of the pigment and the B-segment provides a steric stabilization of the pigment particle against flocculation. The A-segment must be available for interaction with the pigment surface; (2) of sufficient size to provide irreversible adsorption; and (3) not so large as to completely cover the pigment surface or cause collapse of the B-segment. The B-segment must be: (1)
30 of sufficient size to provide steric stabilization (approximately number average molecular weight of 1500 or larger); and (2) compatible with the dispersion media, typically a solvent, and polymeric film forming material used in a coating composition.

The AB block polymer can be prepared by anionic polymerization
35 using conventional polymerization catalysts and solvents. Usually, the A segment

containing polymerized glycidyl (meth)acrylate monomers is prepared first and then the B segment monomers are added and polymerized. It is possible to prepare the B segment initially and then the A segment to form the AB block polymer.

Preferably, the AB block polymer is prepared by using GTP
5 techniques in an inert atmosphere such as nitrogen by charging solvent such as a mixture of tetrahydrofuran and xylene, a catalyst such as tetrabutyl ammonium m-chlorobenzoate and initiator such as 1-methoxy-1-trimethylsiloxy-2-methyl propene into a polymerization vessel and then adding the A segment monomer which is glycidyl (meth)acrylate. When most of the A-segment monomers have
10 reacted typically over 99%, the B-segment monomers are added of alkyl (meth)acrylates, typically methyl methacrylate and butyl methacrylate and the silane blocked hydroxy alkyl (meth)acrylate, typically trimethylsiloxyethyl methacrylate, and polymerization is completed. An aromatic carboxylic acid or an aliphatic carboxylic acid is then added in a sufficient amount to react with all of
15 the glycidyl groups of the polymer and to unblock the silane group of the hydroxy alkyl (meth)acrylate to form the AB block polymer dispersant used in this invention.

Other typical solvents, GTP polymerization catalysts and initiators used to form the AB block polymers are disclosed in the aforementioned GTP
20 patents.

The A-segment of the polymer contains mainly polymerized glycidyl (meth)acrylate monomers, i.e., glycidyl acrylate or glycidyl methacrylate or mixtures thereof Up to 10% by weight, based on the weight of the A segment, of alkyl (meth)acrylate monomers having 1-8 carbon atoms in the alkyl group
25 (described below) can be used in the A segment.

The B-segment of the polymer contains polymerized alkyl (meth)acrylate and silane blocked hydroxy alkyl (meth)acrylate monomers that are subsequently unblocked with an aromatic or aliphatic carboxylic acid.

Typically useful alkyl (meth)acrylates are having 1-12 carbons in
30 the alkyl group can be used in forming the AB block polymer are methyl acrylate, ethyl acrylate, propyl acrylate, isopropyl acrylate, butyl acrylate, pentyl acrylate, hexyl acrylate, 2-ethyl hexyl acrylate, nonyl acrylate, lauryl acrylate, methyl methacrylate, ethyl methacrylate, propyl methacrylate, isopropyl methacrylate, butyl methacrylate, pentyl methacrylate, hexyl methacrylate, 2-ethyl hexyl
35 methacrylate, nonyl methacrylate, lauryl methacrylate and the like and any

mixtures thereof can be used. Other monomers that can be used with the alkyl(meth)acrylate monomers are isobornyl methacrylate and benzyl methacrylate.

Typically useful silane blocked hydroxy alkyl (meth)acrylates
5 having 1 ~ carbon atoms in the alkyl group that can be used are trimethylsiloxyethyl methacrylate, trimethylsiloxyethyl acrylate, trimethylsiloxypropyl methacrylate, trimethylsiloxypropyl acrylate, trimethylsiloxybutyl methacrylate, trimethylsiloxybutyl acrylate and the like. When anionic polymerization is used to form the polymer, hydroxy alkyl
10 (meth)acrylate monomers are used that are not blocked with a silane

Typically useful aromatic and aliphatic carboxylic acids that can be used are p-nitrobenzoic acid, benzoic acid, p-tert.-butylbenzoic acid, diphenylacetic acid, phthalic acid, isophthalic acid, terephthalic acid, naphthaleneacetic acid, p-toluic acid and the like, acetic acid, butyric acid,
15 isobutyric acid, crotonic acid, cyclohexanecarboxylic acid, decanoic acid, lauric acid, oleic acid, palmitic acid, propionic acid, sorbic acid, stearic acid, valeric acid and the like. One preferred acid that forms an excellent dispersant polymer is p-nitrobenzoic acid.

In one preferred embodiment, the AB block polymer contains in
20 the A-segment about 10 to 15 parts by weight glycidyl methacrylate that has been reacted with p-nitrobenzoic acid and in the B-segment about 25-35 parts by weight of methyl methacrylate, 25-35 parts by weight of butyl methacrylate and 1-10 parts by weight of hydroxy ethyl methacrylate.

Suitable other olefinically unsaturated monomers that can be used
25 in minor amounts in the AB block polymer include: acrylamide and methacrylamide and derivatives as alkoxy methyl (meth) acrylamide monomers, such as methacrylamide, N-isobutoxymethyl methacrylamide, and N-methylol methacrylamide; maleic, itaconic and fumaric anhydride and its half and diesters; vinyl aromatics such as styrene, alpha methyl styrene and vinyl toluene; and
30 polyethylene glycol monoacrylates and monomethacrylates.

The AB block polymer is used as a dispersing resin to disperse a wide variety of pigments that are commonly used coating compositions. Typical pigments that are used are metallic oxides such as titanium dioxide, iron oxides of various colors, zinc oxide, carbon black, filler pigments such as talc, china clay,
35 barytes, carbonates, silicates and a wide variety of organic colored pigments such

as quinacridones, copper phthalocyanines, perylenes, azo pigments, indanthrone blues, carbazoles such as carbazole violet, isoindolinones, isoindolones, thioindigo reds, benzimidazolones and the like.

To form the pigment dispersion of this invention the AB block
5 polymer and the pigment to be dispersed is added to a suitable mixing vessel such as an attritor, sand mill, ball mill, two roll mill and the like and then mixed for about 5-150 minutes to form a dispersion having a yield stress of about 0-1,000 Pa (Pascal), a low shear (20 sec-1) viscosity of about 100- 10,000 m. Pas (milli
10 Pascal seconds) and a high shear (1,000 sec-1) viscosity of about 10-1,000 m Pas measured on a Rotvfisco viscometer.

Coatings compositions in which the pigment dispersions of the present invention are used contain a binder preferably of an acrylic-based polymer and a crosslinking agent such as a melamine crosslinking agent, a polyisocyanate crosslinking agent or a blocked polyisocyanate crosslinking agent in an organic
15 liquid carrier which is usually a solvent for the binder constituents or can be a mixture of a solvent/non-solvent to form a NAD (non-aqueous dispersion). The AB block polymers form stable solutions or dispersions, These coating compositions contain about 10-70%, more typically 15-50% by weight of binder, and about 30-90%, more typically 50-85% by weight, of the liquid carrier.
20 Suitable coating compositions are prepared by blending other useful components in accordance with normal paint formulation techniques.

To form a composition which will crosslink under elevated baking temperatures of about 60-180°C for about 5-60 minutes, about 10 to 50%, preferably 15 to 30% by weight, based on the weight of the binder, of an alkylated
25 melamine formaldehyde crosslinking agent having 1-4 carbon atoms in the alkylated group is preferred.

These crosslinking agents are generally partially or fully alkylated melamine formaldehyde compounds and may be monomeric or polymeric as described above. Blocked polyisocyanates can also be used as crosslinking agents.

30 These coating compositions containing a melamine crosslinking agent can contain about 0.1 to 1.0% by weight, based on the weight of a binder, of a strong acid catalyst or a salt thereof to lower curing temperatures and time. Para toluene sulfonic acid or its ammonium salt are preferred catalysts. Other catalysts that can be used are dodecyl benzene sulfonic acid, phosphoric acid and amine or
35 ammonium salts of these acids.

Other film forming polymers can also be used in these coating compositions such as acrylourethanes, polyesters and polyester urethanes, polyethers and polyether urethanes that are compatible with the dispersion of the branched polymer. A polyisocyanate can be used as a crosslinking agent to
5 provide a coating composition that will cure at ambient temperatures.

In addition, coating composition utilizing the dispersion of the present invention may contain a variety of other optional ingredients, including fillers, plasticizers, antioxidants, surfactants and flow control agents.

To improve weatherability of a finish of such coating
10 compositions, an ultraviolet light stabilizer or a combination of ultraviolet light stabilizers can be added in the amount of about 0.1-5% by weight, based on the weight of the binder. The stabilizer may be added for example to a dispersion of this invention containing pigments or may be added directly to the coating composition. Such stabilizers include ultraviolet light absorbers, screeners,
15 quenchers, and specific hindered amine light stabilizers. Also, an antioxidant can be added, in the about 0.1 -5% by weight, based on the weight of the binder.

Typical ultraviolet light stabilizers that are useful include benzophenones, triazoles, triazines, benzoates, hindered amines and mixtures thereof. Specific examples of ultraviolet stabilizers are disclosed in U.S. Patent
20 4,591,533, the entire disclosure of which is incorporated herein by reference.

Such coating composition may also include conventional formulation additives such as flow control agents, for example, "Resiflow" S (polybutylacrylate), I BYK 320 and 325 (high molecular weight polyacrylates); rheology control agents, such as fumed silica and thickeners such as the
25 Acrylsol® copolymers from Rohm & Haas.

Pigment dispersions of the present invention may be utilized in a mono coat or in a pigmented color coat or base coat over which a clear coat is applied to provide a color coat/clearcoat finish. Also, small amounts of pigment dispersion can be added to the clear coat to provide special color or aesthetic
30 effects such as tinting.

Coating compositions formulated with the dispersion of this invention have excellent adhesion to a variety of metallic or non-metallic substrates, such as previously painted substrates, primed substrates cold rolled steel, phosphatized steel, and steel coated with conventional primers by
35 electrodeposition. These coating compositions can be used to coat plastic

substrates such as polyester reinforced fiberglass, reaction injection-molded urethanes and partially crystalline polyamides. In particular, base coat or color coat composition formulated with the dispersion of this invention, provide improved intercoat adhesion between the primer layer and the base coat and improved adhesion to the clear top coat. This improved adhesion results in significantly improved chip resistance of the resulting finish which is very important property for automobile and truck finishes.

Coating compositions formulated with the dispersion of this invention can be applied by conventional techniques such as spraying, electrostatic spraying, dipping, brushing, flowcoating and the like. The preferred techniques are spraying and electrostatic spraying. In OEM applications, the composition is typically baked at 100-150°C for about 15-30 minutes to form a coating about 0.1-3.0 mils thick. When the composition is used as a clearcoat, it is applied over the color coat that may be dried to a tack-free state and cured or preferably flash dried for a short period before the clearcoat is applied. The color coat/clearcoat finish is then baked as mentioned above to provide a dried and cured finish. The present invention is also applicable to non-baking refinish systems, as will be readily appreciated by those skilled in the art.

It is customary to apply a clear topcoat over a basecoat by means of a "wet-on-wet" application, i.e., the topcoat is applied to the basecoat without curing or completely drying the basecoat. The coated substrate is then heated for a predetermined time period to allow simultaneous curing of the base and clear coats.

The following Examples illustrate the invention. All parts, ratios and percentages are on a weight basis unless otherwise indicated. All molecular weights disclosed herein are determined by GPC (gel permeation chromatography) using a polystyrene standard.

EXAMPLE 1

An AB block polymer I was prepared and a pigment dispersion was prepared with the polymer and the pigment dispersion was formulated into a coating composition.

Preparation of AB-block polymer I

To a 5-liter flask fitted with an agitator, condenser, heating mantle, nitrogen inlet, thermocouple and an addition port was added 911 g of

tetrahydrofuran, 4.7 g of p-xylene. 1.5 ml of 1.0 M solution of a catalyst of tetrabutyl ammonium m-chlorobenzoate in acetonitrile was added. 26 g of a 0.149 M solution of an initiator of 1-methoxy-1-trimethylsiloxy-2-methyl propene was injected into the flask. Monomer Feed I GMA (glycidyl methacrylate) 254.5 g (1.79 M) was started at 0.0 minutes and added over 45 minutes. 100 minutes after Feed I was completed (over 99% of the monomer had reacted, Feed II of a mixture of MMA (methyl methacrylate monomer), 448 g (4.48M), BMA (butyl methacrylate monomer) 636.2 g (4.48M) and TMS-HEMA (2-trimethylsiloxyethyl methacrylate monomer), 151.3 g (0.749M) was started and added over 30 minutes. After 300 minutes, 45.3 g water, 800 g propylene carbonate, 269.0 g of p-nitrobenzoic acid (1.61M) and 256 g of butyl acetate were added to the flask and the resulting reaction mixture was held at its reflux temperature and refluxed for 8 hours. The GMA reacted with the p-nitrobenzoic acid and silicone blocking group was removed from the TMS-HEMA. 291 g of butyl acetate was added. The resulting polymer solution has a polymer solids content of 41.5% and the AB block polymer has the following ratio of constituents 12 GMA / 1 30 BMA / 30 MMA / S HEMA where the GMA is the A-segment and BMA/MM/HEMA is the B-segment of the polymer and the polymer has a number average molecular weight of about 14,000 and a weight average molecular weight of about 32,000.

Preparation of AB-block polymer II (control)

This polymer was prepared in an identical manner and with the same constituents as polymer I above except the trimethylsiloxyethyl methacrylate monomer constituent was omitted giving an AB block polymer that does not have hydroxyl groups.

Preparation of a maroon pigment dispersion I

A mixture of 25.3 g of the AB block polymer I (prepared above), 44.7 g butyl acetate and 30.0 g of Perindo Maroon pigment made by Bayer was ground in an 01 attritor for 12 hours at 350 RPM using 3.2 mm stainless steel media. The resulting dispersion has a solids content of 38.8%, a yield stress of 164 dynes/cm², a drawn down transparency (ASTM E 1348-90) of 79% and a haze level of 16.9% at a dry film thickness of 1.0 mil.

Preparation of maroon pigment dispersion II

The same pigments dispersion was formed as above using the same constituents except that AB-block polymer I was replaced with AB-block polymer II (control). The resulting pigment dispersion has a solids content of 40.5%, a
5 yield stress of 3.6 dynes/cm², draw down transparency of 79% and a haze level of 5.7% at a dry film thickness of 1.0 mil.

Preparation of Red Coating Composition I

A red metallic high solids basecoat coating composition was
10 prepared by mixing together the following constituents: 252.3 g of acrylic microgel resin (50% nv - non volatile solids), 98.3 g of polyester resin (80% nv), 206.3 g of fully methylated melamine formaldehyde resin (100% nv), 13.9 g of acid catalyst solution (38% nv), 23.5 g of W screener solution (40% nv), 14.7g of UV stabilizer solution (40% nv) and 31.2 g of methanol with 227.6 g of maroon
15 pigment dispersion I (prepared above), 6.3 g of red iron oxide pigment dispersion and 90.7 g of aluminum flake dispersion. The resulting coating composition contained 20.9 parts by weight of dry pigment, 100 parts by weight of dry binder, and the pigment blend weight ratio was 68.3 part maroon pigment/3.3 parts red iron oxide pigment/23.3 parts aluminum flake pigment.

20

Preparation of Red Coating Composition II (control)

A red high solids basecoat coating composition was prepared using the identical constituents as in Composition I above except the maroon pigment dispersion II made with AB-block polymer II (control) was used instead of the
25 maroon pigment dispersion made with AB-block polymer I.

Preparation of jet black pigment dispersion I

A mixture of 34.10 g of AB-block polymer I (prepared above), 50.9 g of butyl acetate and 15 g of jet black pigment, FW-200, made by Degussa
30 was ground in a 01 attritor for 24 hours at 350 RPM using 3.2 mm stainless steel media. The resulting dispersion has a solids content of 29.7%, a viscosity of 200 centipoise at 1 rpm and 190 centipoise at 50 rpm using a Brookfield viscometer and a drawdown gloss of 123 measured at 60 degrees.

Preparation of jet black pigment dispersion II (control)

The same jet black pigment dispersion was formed as above using the same constituents except that AB-block polymer I was replaced with AB-block polymer II (control). The resulting pigment dispersion has a solids
5 content of 29.4%, a viscosity of 100 centipoise at 1 rpm and 80 centipoise at 50 rpm using a Brookfield viscometer and drawdown gloss of 120 at 60 degrees.

Preparation of Jet Black Coating Composition III

A black high solids basecoat coating composition was prepared by
10 mixing together the following constituents: 118.6 g of acrylic microgel resin (50% nv - non volatile solids), 139.0 g of polyester resin (80% nv), 160.5 g of fully methylated melamine formaldehyde resin (100% nv), 10.8 g of acid catalyst solution (38% nv), 18.2g of W screener solution, 11.4 g W stabilizer solution (40% nv) and 102 g xylene and 24.6 g methanol with 91.3 g of black pigment
15 dispersion I (prepared above). The resulting coating composition contained 3 parts by weight of dry black pigment to 100 parts by weight of dry binder.

Preparation of Jet Black Coating Composition IV (control)

A black high solids basecoat coating composition was prepared
20 using the identical constituents as in Composition m above except the jet black pigment dispersion II made with AB-block polymer II (control) was used instead of the jet black pigment dispersion made with AB-block polymer I.

Preparation of Clear Coating Composition

25 A high solids acrylic clear coating composition was prepared by mixing together the following ingredients: 268.1 g of acrylic copolymer resin (71.5% nv), 155.5 g of acrylic NAD resin (65.5% nv), 198.6 g of fully methylated melamine formaldehyde resin, 11.7 g of acid catalyst solution, 13.5 g of W screener solution, 6.1 g of W stabilizer solution, 1.2 g of flow control additive, 0.8
30 g of silicone anticratering additive, 86.7 g of xylene and 18.8 g of methanol. The resulting clear coating composition contained 62% binder solids and was sprayed at a spray viscosity of 28 seconds/#4 Ford cup.

Testing of Above Prepared Coating Compositions

Standard Conditions

Each of the above prepared Coating Compositions I-IV were sprayed onto separate phosphated, electrocoated and primed steel panels and each coated with the above Clear Coating Composition. Cold rolled steel panels pretreated with zinc phosphate were electrocoated with about 0.8-1.0 mils of an electrodeposition primer of an epoxy based resin crosslinked with a polyisocyanate and baked for 30 minutes at about 170°C and about 0.8 mils of a primer surfacer was spray applied and baked for 20 minutes at about 149°C. Each of the above prepared Coating Compositions I-IV were reduced to a spray viscosity of 17 second/#4 Ford cup with xylene and were spray applied to separate panel. The compositions were applied to a dry film thickness of about 0.5-0.7 mils in two coats with a 60 second air dry time between each coat and were allowed to air dry for 3 minutes before the Clear Coating Composition was applied. The Clear Coating Composition was applied in 2 coats to a dry film thickness of 1.8-2.0 mils, allowed to air dry for 10 minutes and then baked for 17 minutes at 130°C.

Repair Conditions

A separate set of panels prepared as above under standard conditions was repaired by recoating the panels to the same film thickness using the same basecoat and clear coat as above and rebaking at the same time and temperatures as used in the standard conditions. No sanding or other surface preparation was done to the panels before the panels were recoated.

The above prepared panels were subjected to the following test:

Gravelometer Chip Resistance Test (ASTM D-3170-87),

Rating (based on number of chips panel): 10 - zero chips, 9 - 1 chip, 8 - 2-4 chips, 7 - 5-9 chips, 6 - 10-24 chips, 5 - 25-49 chips, 4 - 50-74 chips, 3 - 75-99 chips, 2 - 100-149 chips, 1 - 150-250 chips, 0 - >250 chips.

Rating (based on chip size)

A = < 1mm

B = 1-3 mm

C = 3-6 mm

D = > 6mm

Crosshatch Tape Adhesion Test (ASTM D-3359B)

Rating 0% = no loss of adhesion, 100% = complete failure

The results of the tests were as follows:

Basecoating Composition	Test Condition	Chip Resistance	% Adhesion Loss
Red Basecoating I (Invention AB block polymer)	Standard	4 BA	0
	Repair	4 BA	0
Red Basecoating II (AB block polymer Control)	Standard	3 BA	0
	Repair	4 BC	10
Black Basecoating III (Invention AB block polymer)	Standard	4 AB	0
	Repair	4 AB	0
Black Basecoating IV (AB block polymer Control)	Standard	4 AB	0
	Repair	3 BA	9

- 5 The above data shows that the intercoat adhesion under repair conditions is significantly improved by using coating compositions formulated with dispersions of the AB block polymer of the invention

FA-0736

CLAIMS

We claim:

1. A pigment dispersion useful for forming coating composition comprising dispersed pigment, a carrier liquid and an AB-block polymer dispersant (binder);
5 the AB block polymer has a number average molecular weight of about 5,000 - 20,000 and consists of 20-80% by weight of a polymeric A segment and correspondingly 80-20% by weight of a polymeric B segment; wherein
10 the polymeric A segment of the block polymer consists essentially of polymerized glycidyl (meth)acrylate monomers reacted with an acid selected from the group consisting of aromatic carboxylic acids and aliphatic carboxylic acids; and
the B segment consists essentially of polymerized alkyl
15 (meth)acrylate monomers having 1 - 12 carbon atoms in the alkyl group, hydroxy alkyl (meth)acrylate monomers having about 1-4 carbon atoms in the alkyl group; and
wherein the weight ratio of pigment to binder in the dispersion is about 1/100 -
20 200/100.
2. The coating composition of claim 1 in which the AB block polymer is prepared by group transfer polymerization.
- 25 3. The coating composition of claim 2 wherein the polymeric A segment consists of polymerized glycidyl methacrylate reacted with an aromatic carboxylic acid.
- 30 4. The dispersion of claim 3 wherein the polymeric A segment of the AB block polymer consists of polymerized monomers of glycidyl methacrylate reacted with para nitrobenzoic acid.
5. The dispersion of claim 2 wherein the polymeric B segment of the AB block polymer consists of polymerized monomers of alkyl

having 14 carbon atoms in the alkyl groups and hydroxy alkyl methacrylates having 2-4 carbon atoms in the alkyl groups.

6. The dispersion of claim 5 in which the polymeric B segment
5 of the AB block polymer consists of polymerized monomers of butyl methacrylate, methyl methacrylate and hydroxy ethyl methacrylate.

7. The dispersion of claim 2 in which the AB block polymer
10 consists of a polymeric A segment of polymerized monomers of glycidyl methacrylate reacted with para nitrobenzoic acid and the polymeric B segment consists of polymerized monomers of butyl methacrylate, methyl methacrylate and polymerized hydroxy ethyl methacrylate in a weight ratio of about 10-15//25-35/25-35/1-10.

8. A coating composition which comprises an organic liquid
15 carrier and a film forming binder and about 1-50% by weight of the pigment dispersion of claim 1.

9. A process for preparing the dispersion of claim 2 in which
20 the AB block polymer is formed by the process comprising
(a) preparing the A segment of the polymer in an organic solvent in the presence of a group transfer polymerization catalyst and initiator by polymerizing glycidyl (meth)acrylate monomers;
(b) polymerizing B segment monomers of alkyl (meth)acrylate having
25 1-12 carbon atoms in the alkyl group and silane blocked hydroxy alkyl (meth)acrylate having 1-4 carbon atoms in the alkyl group in the presence of the A-segment of the polymers to form the AB block polymer having a weight average molecular weight of about 5,000-20,000; and
(c) reacting the polymer with an acid selected from the group of
30 aromatic carboxylic acids and aliphatic carboxylic acids to react the glycidyl groups and remove the silicone blocking groups from the polymer; and
(d) dispersing pigment in the AB block polymer dispersion to form a pigment dispersion.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 98/14835

A. CLASSIFICATION OF SUBJECT MATTER

C 09 D 153/00

According to International Patent Classification (IPC) or to both national classification and IPC⁶

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C 09 D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4812517 A (WEST, M.W.J.) 14 March 1989 (14.03.89), claims.	1
	--	
A	EP 0218436 A2 (E.I. DU PONT DE NEMOURS AND COMPANY) 15 April 1987 (15.04.87), claims.	1

☐ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search
08 October 1998

Date of mailing of the international search report

11 11. 1998

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

PAMMINGER e.h.

ANHANG

zum Internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US 98/14835 SAE 201488

In diesem Anhang sind die Mitglieder
der Patentfamilien der in obenge-
nannten internationalen Recherchenbericht
angeführten Patentedokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visée ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

In Recherchenbericht angeführtes Patentedokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A	4812517	14-03-89	CA A1 1304852 EP A2 323181 EP A3 323181 JP A2 1204914	07-07-92 05-07-89 03-10-90 17-08-89
EP A2	218436	15-04-87	AT E 69057 AU A1 63259786 AU B2 584848 BR A 8604644 CA A1 1247272 DE C0 3682251 DK A0 4630786 DK A 4630786 EP A3 218436 EP B1 218436 ES AF 2002014 HK A 2281792 JP A2 62081459 JP B4 6092473 KR B1 9508518 MX B 164882 NO A0 863873 NO A 863873 NO B 167926 NO C 167926 SG A 1017791 US A 4636226 ZA A 8607454	15-11-91 02-04-87 01-06-89 09-06-87 20-12-88 05-12-91 29-09-86 31-03-87 22-02-89 30-10-91 01-07-88 24-04-92 14-04-87 16-11-94 31-07-93 29-09-92 29-09-86 31-03-87 16-09-91 27-12-91 17-01-92 07-04-87 25-05-88

